

Factory Address: No.66 Yong Wei Road, Bai Zhou edge, Guan Long Road, Dong Cheng District, Dong guan City, Guangdong Province, China

TEL: 0769-22653892

FAX: 0769-22653316 Version: Oct. 2, 2017

Sulphonic acid amine catalyst $T{-}3218/T{-}5218$

1.Description

Description: T-3218/T-5218 is Sulphonic acid amine catalyst which could be used as catalyst for Powdelink 1174 system. T-3218 suitable for exterior small textured wrinkle finish at dosage of 0.5-1.5%;T-5218 for exterior bigger textured wrinkle finish at dosage of 0.2-0.4%.

2. Typical physical data

Appearance	White fine powder
Solid content(%)	>99%

3.Suggested formula

Polyurethane resin (hydroxyl value :35	560	560
\pm 5such as : EL-1000H)		
Curing gent T-1174	38	38
Catalyst T-3218	5-15	/
Catalyst T-5218	/	2-4
Levelling agent T-988	8	8
Benzoin	4	4
Carbon black	10	10
Barium sulfate	360	360
Curing condition: $200^{\circ}C \times 15 min$	T-55 0.2-0.4% post-added can	MCC 0.2-0.4% post-added in
	get bigger texture.	can get bigger wrinkle finish

4. Characteristics

①Normally PU resin content 55-65%, more bigger and good performance wrinkle finish

depends on higher resin content.

@Polyurethane (hydroxyl value 35±5) combine with curing agent T-1174 chemical ratio is 94/6; curing gent T-1530 IS 83/17;1% T-1530 replace of T-1174 could be used to enlarge the texture and increase the gloss of the film

32-4% epoxy resin can be used to enlarge the texture and reduce the gloss of film.

5. Package and storage:

Packaging with PE lined Kraft paper bags, Net weight 25kg per bag. Store in cool and dry place to avoid moisture. According to our experience, the shelf life of this product is at least 2 years when ambient temperature below 30 °C.