



Shanghai Suo Shi Chemical Industrial Co.Ltd

Dongguan Suoshi New Material Co.,Ltd

Factory Address : No.66 Yong Wei Road ,Bai Zhou edge,Guan Long Road, Dong
Cheng District, Dong guan City,Guangdong Province , China

TEL : 0769-22653892

FAX : 0769-22653316

Version: Oct.13.2016

Floating agent T-55

1. Description: dry-blending with additive T-55, modified acrylate polymer , with lower surface tension. It is used for making the Hammertone and Structure finish of powder coatings with dry-blending .

2. Specification:

Appearance:off-white fine powder

Soft point: 105~125°C

Solid content: >99%

3. Usage

Dry-blending with base coats by 0.2-0.4%.

4. Storage

Polyethylene lining, net weight 25KG caveat; stored in a cool and dry place to avoid moisture absorption. In the < 30 °C is valid for two years at room temperature