



Shanghai Suo Shi Chemical Industrial Co.Ltd
Dongguan Suoshi New Material Co.,Ltd

Factory Address: No.66 Yong Wei Road ,Bai Zhou edge,Guan Long Road, Dong
Cheng District, Dong guan City,Guangdong Province , China

TEL: 0769-22653892

FAX: 0769-22653316

Version: Nov. 18, 2015

Curing accelerator T-61(TDS)

1.Description

T-61 is a catalyst with resin as carrier. The amount of T-61 can be used in powder coating to lower curing temperature or shorten the curing time in polyester/epoxy hybrid and polyester/TGIC system, which contains active ingredient about 10%. Excellent resistance to yellow and good dispersion, does not affect the flow and gloss of the coating.

2. Typical physical data

Appearance	White fine powder
Soft range(°C)	100-120
Solid content(%)	>99
Acid value(mgKOH/g)	30-35

3.Method and dosage

0.3-0.8% of total formula for extrusion.

4. package and storage:

Polyethylene lining, net weight 25KG caveat; stored in a cool and dry place to avoid moisture absorption. In the < 30 °C is valid for two years at room temperature