



Shanghai Suo Shi Chemical Industrial Co.Ltd

Dongguan Suoshi New Material Co.,Ltd

Factory Address: No.66 Yong Wei Road ,Bai Zhou edge,Guan Long Road, Dong
Cheng District, Dong guan City,Guangdong Province ,
China

TEL: 0769-22653892

FAX: 0769-22653316

Version: Nov. 18, 2014

Curing accelerator T-66

1.Description

T-66 is a typical accelerator can be used in powder coating to lower curing temperature or shorten the curing time, which contains active ingredient 10% about. Excellent resistance to yellow and dispersion, does not affect the flow and gloss of the coating.

2. Typical physical data

Appearance	White crystal powder
Soft range(°C)	200-210
Solid content(%)	>99

3.Method and dosage

0.05-0.2% of total formula for extrusion.

4. package and storage:

Packaging with PE lined Kraft paper bags, Net weight 25kg per bag. Store in cool and dry place to avoid moisture. According to our experience, the shelf life of this product is at least 2 years when ambient temperature below 30 °C.